

**AMENDMENTS TO THE CLAIMS**

**This listing of claims will replace all prior versions and listings of claims in the application:**

**LISTING OF CLAIMS:**

1. and 2. (canceled).

3. (previously presented): A method for producing an RE-containing alloy represented by formula  $R(T_{1-x}A_x)_{13-y}$  (wherein R represents at least one species selected from among La, Ce, Pr, Nd, Sm, Eu, Tb, Dy, Ho, Tm, Yb, Gd, and Lu; T represents at least one species selected from among Fe, Co, Ni, Mn, Pt, and Pd; and A represents at least one species selected from among Al, As, Si, Ga, Ge, Mn, Sn, and Sb ( $0.05 \leq x \leq 0.2$ ; and  $-1 \leq y \leq 1$ )) comprising:

a melting step of melting alloy raw materials at 1,200 to 1,800°C; and

a solidification step of solidifying the molten metal produced through the above melting step by rapidly quenching the molten metal, to thereby form the RE-containing alloy, wherein the solidifying is performed at a cooling rate of  $10^2$  to  $10^4$ °C/second, as measured at least within a range of the temperature of the molten metal to 900°C, and

wherein in the solidification step, the molten metal is rapid-quenched through any of strip casting, centrifugal casting with a tundish having a rotatable disk, and centrifugal casting.

4. (previously presented): A method for producing the RE-containing alloy according to claim 3, wherein the solidifying is performed by rapidly quenching the molten metal through strip casting, to obtain strips having a thickness of 0.1 to 2.0 mm.

5. (previously presented): A method for producing an RE-containing alloy represented by formula  $R(T_{1-x}A_x)_{13-y}$  (wherein R represents at least one species selected from among La, Ce, Pr, Nd, Sm, Eu, Tb, Dy, Ho, Tm, Yb, Gd, and Lu; T represents at least one species selected from among Fe, Co, Ni, Mn, Pt, and Pd; and A represents at least one species selected from among Al, As, Si, Ga, Ge, Mn, Sn, and Sb ( $0.05 \leq x \leq 0.2$ ; and  $-1 \leq y \leq 1$ )) comprising:

melting alloy raw materials at 1,200 to 1,800°C;

solidifying the molten metal produced through the above melting step by rapidly quenching the molten metal, to thereby form an RE-containing alloy, wherein the solidifying is performed at a cooling rate of  $10^2$  to  $10^4$ °C/second, as measured at least within a range of the temperature of the molten metal to 900°C, and

heat treating by heating at 900 to 1,200°C the RE-containing alloy that is produced through the solidifying, to thereby form an  $\text{NaZn}_{13}$  phase.

6. (previously presented): The method for producing an RE-containing alloy according to claim 5, wherein the  $\text{NaZn}_{13}$  phase is formed through the heat treating, which is performed for a period of from one minute to 200 hours.

7. (canceled).

8. (previously presented): An RE-containing alloy which is obtainable through the method of any one of claims 3 to 4.

9. (original): An RE-containing alloy, which is represented by the formula  $R(T_{1-x}A_x)_{13-y}$  (wherein R represents at least one species selected from among La, Ce, Pr, Nd, Sm, Eu, Tb, Dy, Ho, Tm, Yb, Gd, and Lu; T represents at least one species selected from among Fe, Co, Ni, Mn, Pt, and Pd; and A represents at least one species selected from among Al, As, Si, Ga, Ge, Mn, Sn, and Sb ( $0.05 \leq x \leq 0.2$ ; and  $-1 \leq y \leq 1$ )), and which comprises an R-rich phase, having a relatively high rare earth metal (R) content, and an R-poor phase, having a relatively low rare earth metal (R) content, wherein the R-rich phase and the R-poor phase are dispersed at a phase spacing of 0.01 to 100  $\mu\text{m}$ .

10. (original): An RE-containing alloy, which is represented by the formula  $R(T_{1-x}A_x)_{13-y}$  (wherein R represents at least one species selected from among La, Ce, Pr, Nd, Sm, Eu, Tb, Dy, Ho, Tm, Yb, Gd, and Lu; T represents at least one species selected from among Fe, Co, Ni, Mn, Pt, and Pd; and A represents at least one species selected from among Al, As, Si, Ga, Ge, Mn, Sn, and Sb ( $0.05 \leq x \leq 0.2$ ; and  $-1 \leq y \leq 1$ )), wherein the alloy has an  $\text{NaZn}_{13}$  phase content of at least 90 vol.%.

11. (original): A magnetostrictive device provided from the RE-containing alloy according to claim 10.

12. (original): A magnetic refrigerant provided from the RE-containing alloy according to claim 10.

13. (withdrawn): An RE-containing alloy, which is represented by a compositional formula of  $R_rT_tA_a$  (wherein R represents at least one rare earth element selected from among La, Ce, Pr, Nd, Sm, Eu, Tb, Dy, Ho, Tm, Yb, Gd, and Lu; T collectively represents transition metal elements containing at least Fe atoms, a portion of the Fe atoms being optionally substituted by at least one species selected from among Co, Ni, Mn, Pt, and Pd; A represents at least one element selected from among Al, As, Si, Ga, Ge, Mn, Sn, and Sb; and r, t, and a have the following relationships:  $5.0 \text{ at.}\% \leq r \leq 6.8 \text{ at.}\%$ ,  $73.8 \text{ at.}\% \leq t \leq 88.7 \text{ at.}\%$ , and  $4.6 \text{ at.}\% \leq a \leq 19.4 \text{ at.}\%$ ) and having an alloy microstructure containing an  $\text{NaZn}_{13}$ -type crystal structure in an amount of at least 85 mass% and  $\alpha$ -Fe in an amount of 5-15 mass% inclusive.

14. (withdrawn): A method for producing an RE-containing alloy powder, comprising pulverizing, by mechanical means, the RE-containing alloy according to claim 13 to a powder having a mean particle size of 0.1  $\mu\text{m}$  to 1.0 mm.

15. (withdrawn): An RE-containing alloy powder comprising an RE-containing alloy according to claim 13, which has a mean particle size of 0.1  $\mu\text{m}$  to 1.0 mm.

16. (withdrawn): A magnetic refrigerant comprising the sintered RE-containing alloy powder according to claim 15, wherein the Curie temperature of the magnetic refrigerant has been controlled through absorption of hydrogen in the sintered RE-containing alloy.

17. (withdrawn): A method for producing a sintered RE-containing alloy, which comprises compacting an RE-containing alloy powder produced through a method for producing an RE-containing alloy powder according to claim 14, and sintering the compact.

18. (withdrawn): The method for producing a sintered RE-containing alloy according to claim 17, wherein the sintering is performed at 1,200°C to 1,400°C.

19. (withdrawn): The method for producing a sintered RE-containing alloy according to claim 17 or 18, wherein, after completion of sintering the RE-containing alloy powder, the sintered alloy is maintained in a hydrogen atmosphere at 200°C to 300°C, to thereby absorb hydrogen into the sintered alloy.

20. (withdrawn): A sintered RE-containing alloy, which is formed by compacting the RE-containing alloy powder according to claim 15, and sintering the compact.

21. (withdrawn): A magnetostrictive material comprising the sintered RE-containing alloy according to claim 20, wherein the Curie temperature of the magnetostrictive material has been controlled through absorption of hydrogen into the sintered RE-containing alloy.

22. (withdrawn): A magnetic refrigerant comprising the sintered RE-containing alloy as recited in claim 20, wherein the Curie temperature of the magnetic refrigerant has been controlled through absorption of hydrogen into the sintered RE-containing alloy.

23. (previously presented): The method for producing an RE-containing alloy according to claim 3, wherein, in the melting step, the alloy raw material is melted in an inert gas atmosphere at 0.1 to 0.2 MPa.